



ANSI/NACE TM0416-2023/
ISO 22858:2020

International Standard
**ANSI/NACE TM0416-2023/ISO
22858:2020**

Identical to ISO 22858:2020

**Corrosion of metals and alloys — Electrochemical
measurements — Test method for monitoring
atmospheric corrosion**

An American National Standard
Approved April 12, 2023

Reference number

ANSI/NACE TM0416-2023/ISO 22858:2020

© AMPP/ISO 2023

© 2023 Association for Materials Protection and Performance (AMPP). All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted, in any form or by any means (electronic, mechanical, photocopying, recording, or otherwise) without the prior written permission of AMPP.

Corrosion of metals and alloys — Electrochemical measurements — Test method for monitoring atmospheric corrosion

COPYRIGHT PROTECTED DOCUMENT

These materials are subject to copyright claims of ISO and AMPP. No part of this publication may be reproduced in any form, including an electronic retrieval system, without the prior written permission of AMPP. All requests pertaining to the ANSI/NACE TM0416/ISO 22858 standard should be submitted to AMPP. All rights reserved.

International Organization for Standardization (ISO)
ISO Central Secretariat
BIBC II
Chemin de Blandonnet 8
CP 401
1214 Vernier, Geneva
Switzerland
Tel. + 41 22 749 0111
Fax + 41 22 749 0947
Web: www.iso.ch

Association for Materials Protection and Performance (AMPP)
15835 Park Ten Place
Houston, TX 77084-5145
Tel. +1 281-228-6223
Fax +1 281-228-6300
Web: www.ampp.org

Printed in the U.S.A. by AMPP

AMPP values your input. To provide feedback on this standard, please contact: standards@ampp.org

Corrosion of metals and alloys — Electrochemical measurements — Test method for monitoring atmospheric corrosion

Foreword	6
Introduction	7
1	Scope	7
2	Normative references	7
3	Terms and definitions	7
4	Summary of sensors	8
5	Free corrosion current sensor	8
5.1	Free corrosion current sensor description	8
5.2	Sensor geometry	9
5.3	Uniform corrosion current measurement	9
5.3.1	Use and conditions for uniform corrosion measurement	9
5.3.2	Method 1 — Sine wave excitation	9
5.3.3	Method 2 — Triangle wave excitation	9
5.3.4	Method 3 — Potential step excitation	9
5.4	Localized corrosion current measurement	9
5.5	Free corrosion rate and total free corrosion for sensors without coatings	10
5.5.1	Free corrosion current and current density	10
5.5.2	Free corrosion penetration rate	10
5.5.3	Free corrosion mass loss rate	10
5.5.4	Total free corrosion mass loss and corrosion penetration	10
5.6	Free corrosion current and total charge for sensors with coatings	11
5.6.1	Use and conditions for free corrosion measurements with coatings	11
5.6.2	Free corrosion current for a coated sensor	11
5.6.3	Free corrosion total charge for a coated sensor	11
5.7	Free corrosion sensor preparation	11
5.7.1	Considerations for free corrosion sensor surface preparation	11
5.7.2	Free corrosion sensors without coatings	11
5.7.3	Free corrosion sensors with coatings and surface treatments	11
5.8	Specification and inspection — Free corrosion sensors	12
5.8.1	Visual inspection	12
5.8.2	Sensor range and span	12
5.8.3	Electrical verification tests	13
5.8.4	Corrosion verification tests	13
6	Galvanic corrosion current sensor	13
6.1	Galvanic corrosion current sensor description	13

6.2	Sensor geometry.....	13
6.3	Galvanic corrosion current measurements	14
6.3.1	Methods for galvanic corrosion current measurement.....	14
6.3.2	Method 1 — Zero-resistance ammeter	14
6.3.3	Method 2 — Precision resistor	14
6.4	Galvanic corrosion rate and total galvanic corrosion without coatings.....	14
6.4.1	Galvanic corrosion current	14
6.4.2	Galvanic corrosion rate for mass loss and corrosion penetration	14
6.4.3	Total galvanic corrosion mass loss and corrosion penetration.....	14
6.5	Galvanic corrosion rate and total galvanic corrosion with coatings.....	15
6.5.1	Use and conditions for galvanic corrosion measurements with coatings.....	15
6.5.2	Galvanic mass loss corrosion rate for a coated sensor	15
6.5.3	Total galvanic mass loss for a coated sensor.....	15
6.6	Galvanic corrosion sensor preparation	15
6.6.1	Considerations for galvanic corrosion sensor preparation.....	15
6.6.2	Galvanic corrosion sensors without coatings	15
6.6.3	Galvanic corrosion sensors with coatings and surface treatments	15
6.7	Specification and inspection — Galvanic corrosion sensors.....	15
6.7.1	Visual, span and range inspection	15
6.7.2	Electrical verification tests.....	15
6.7.3	Corrosion verification tests.....	16
7	Thin film conductance sensors.....	16
7.1	Conductance sensor description	16
7.2	Sensor geometry.....	16
7.3	Surface conductance measurement method	16
7.4	Surface conductance sensor preparation	16
7.5	Specification and inspection — Conductance sensor.....	16
7.5.1	Visual, span and range inspection	16
7.5.2	Electrical verification tests.....	17
7.5.3	Conductive solution verification tests	17
8	Coating barrier property sensors.....	17
8.1	Coating barrier property sensor description.....	17
8.2	Coating barrier property measurements	17
8.3	Coating barrier property sensor preparation	17
8.3.1	Sensor preparation for coating.....	17
8.3.2	Coating test condition.....	17
8.4	Specification and inspection — Coating barrier property sensor	18
8.4.1	Visual, span and range inspection	18
8.4.2	Electrical measurements.....	18
8.4.3	Sensing system impedance verification tests	18

8	Coating barrier property sensors.....	18
9	Atmospheric testing with electrochemical sensors.....	18
	9.1 Types of atmospheric tests	18
	9.2 Test arrangement.....	18
	9.3 Test duration.....	18
	9.4 Sensor selection.....	18
	9.5 Sampling time interval.....	18
	9.6 Date and time information.....	19
10	Test report.....	19
	10.1 Test report guidance.....	19
	10.2 Sensor information.....	19
	10.3 Surface preparation.....	19
	10.4 Test description	19
	10.5 Sensor inspection.....	19
	10.6 Data storage.....	19
	Annex A (informative) Example images of electrochemical sensors.....	20
	Annex B (informative) Equivalent circuit analysis for two-electrode measurements.....	22
	Annex C (informative) Example of reporting information.....	24
	Bibliography	25

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 156, *Corrosion of metals and alloys*. Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The purpose of this document is to provide instructions on the use of electrochemical sensors for monitoring atmospheric corrosion. These sensors are used to measure thin film electrolyte conductance, corrosion current or coating condition over long periods. This method permits the instantaneous evaluation of corrosion current that can be related to specific environmental conditions in real time. The instantaneous corrosion current measurements are not accessible using electrical resistance sensors or mass loss techniques. The technology described in this document complements other standard techniques for assessing atmospheric corrosion such as mass loss coupons, electrical resistance sensors or coated test panels (see ISO 8407 and ISO 4628-8). These continuous records of material condition can be useful for studying atmospheric corrosion, evaluating materials or managing assets^{[21][22][23][24][25][26][27][28][29]}.

This document was developed based on ANSI/NACE TM0416-2016.

This document is relevant to alloy and coating manufacturers and users in transportation, chemical process, energy and infrastructure applications.

Corrosion of metals and alloys — Electrochemical measurements — Test method for monitoring atmospheric corrosion

1. Scope

This document specifies a test method for atmospheric corrosion measurements, using two-electrode electrochemical sensors.

It is applicable to measurements of the corrosion rate of uncoupled metal surfaces (i.e. “free” corrosion rate), galvanic corrosion rate, conductance of thin film solutions and barrier properties of organic coatings. It specifies electrochemical sensors that are used with or without organic coatings. The sensors are applicable to corrosion measurements made in laboratory test chambers, outdoor exposure sites and service environments.

2. Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4618, Paints and varnishes — Terms and definitions

ISO 4628 (all parts), Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance

ISO 8044, Corrosion of metals and alloys — Vocabulary

ISO 9223, Corrosion of metals and alloys — Corrosivity of atmospheres — Classification, determination and estimation

3. Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618, ISO 4628 (all parts), ISO 8044, ISO 9223 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform, available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 electrical resistance sensor

device for measuring corrosion involving measurement of the ratio of the potential difference along a conductor and the current through the conductor

Note 1 to entry: ISO 15091:2019, 3.1, defines “electrical resistance” as the “ratio of the potential difference along a conductor and the current through the conductor”.

3.2 electrochemical sensor

device for measuring corrosion involving anodic and cathodic reactions

Note 1 to entry: ISO 8044:2020, 4.1, defines “electrochemical corrosion” as “corrosion involving at least one anodic reaction and one cathodic reaction”.