



AEROSPACE MATERIAL SPECIFICATION	AMS5664™	REV. G
	Issued 1965-09 Reaffirmed 2006-04 Revised 2022-08	
Superseding AMS5664F		
Nickel Alloy, Corrosion- and Heat-Resistant, Bars, Forgings, Extrusions, Rings, and Stock for Forgings and Rings 52.5Ni - 19Cr - 3.0Mo - 5.1Cb (Nb) - 0.90Ti - 0.50Al - 18Fe Consumable Electrode or Vacuum Induction Melted 1950 °F (1066 °C) Solution Heat Treated, Precipitation Hardenable (Composition Similar to UNS N07718)		

RATIONALE

AMS5664G is the result of a Five-Year Review and update of the specification. The revision prohibits unauthorized exceptions (3.5.1.2.1.4, (removing) 3.5.1.1.1.4, 3.9, 4.4.1.1, 4.4.3, 5.2.1.1, 8.5), updates title to match the scope, updates the description of size and size limits (1.1, 3.5.1.1.1.1, 3.5.1.2.1), revises composition requirement and reporting (3.1, 3.1.1) adds cold finished bars and associated requirements (3.3.1), updates information for extrusions (3.3.2, 8.6), provides for consistent heat treatment requirements between similar specs (3.4), adds strain rate control during testing (3.5.1.2.1.3), adds forging stock options (4.4.2), and allows prior revisions (8.4).

1. SCOPE

1.1 Form

This specification covers a corrosion- and heat-resistant nickel alloy in the form of bars, forgings, flash welded rings in the solution heat treated condition, Product covered by this specification is limited to 10.00 inches (254 mm) and under in nominal diameter or maximum cross-sectional dimension, between parallel sides (thickness) and 78.54 square inches (503 cm²) in cross-sectional area. Stock may be of any size for forging or flash welded rings.

1.2 Application

These products have been used typically for rotating and structural parts requiring high strength at cryogenic temperatures and for short-time service up to 1000 °F (538 °C) and oxidation resistance up to 1800 °F (982 °C), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE International Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2022 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS5664G/>