



<b>AEROSPACE MATERIAL SPECIFICATION</b>	<b>AMS6910™</b>	<b>REV. D</b>
	Issued	2004-01
	Revised	2022-08
Superseding AMS6910C		
Titanium Alloy Bars, Forgings and Forging Stock 8Al - 1Mo - 1V Duplex Annealed (Composition similar to UNS R5-310)		

## RATIONALE

AMS6910D results from a Five-Year Review and update of this specification with changes to update wording to prohibit unauthorized exceptions (3.5.1.1.5, 8.5), relocate definitions (2.3) and information regarding data and statistical analysis (3.5.1.1.6), update applicable documents (Section 2), and ordering information (8.6).

### 1. SCOPE

#### 1.1 Form

This specification covers a titanium alloy in the form of bars up through 4.000 inches (101.60 mm), inclusive, in nominal diameter or least distance between parallel sides, forgings of thickness up through 4.000 inches (101.60 mm), inclusive, and stock for forging of any size (see 8.6).

#### 1.2 Application

This alloy has been used typically for parts requiring strength up to 800 °F (427 °C), but usage is not limited to such applications.

1.2.1 Certain processing procedures and service conditions may cause these products to become subject to stress-corrosion cracking; ARP982 recommends practices to minimize such conditions.

### 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

#### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS2241 Tolerances, Corrosion- and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

AMS2249 Chemical Check Analysis Limits, Titanium and Titanium Alloys

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2022 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: [CustomerService@sae.org](mailto:CustomerService@sae.org)  
<http://www.sae.org>

SAE WEB ADDRESS:

**For more information on this standard, visit**  
<https://www.sae.org/standards/content/AMS6910D/>