

Wet Abrasive Blast Cleaning

©2023 Association for Materials Protection and Performance (AMPP). All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted, in any form or by any means (electronic, mechanical, photocopying, recording, or otherwise) without the prior written permission of AMPP.

Wet Abrasive Blast Cleaning

This AMPP technical report represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the technical report or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this technical report. Nothing contained in this AMPP technical report is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by letters patent, or as indemnifying or protecting anyone against liability for infringement of letters patent. This technical report represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this technical report intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this technical report in specific instances. AMPP assumes no responsibility for the interpretation or use of this technical report by other parties and accepts responsibility for only those official AMPP interpretations issued by AMPP in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this AMPP technical report are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this technical report prior to its use. This AMPP technical report may not necessarily address all potential health and safety problems, or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this technical report. Users of this AMPP technical report are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities, if necessary to achieve compliance with any existing applicable regulatory requirements prior to the use of this technical report.

CAUTIONARY NOTICE: AMPP technical reports may be revised or withdrawn at any time in accordance with AMPP standards committee procedures. The user is cautioned to obtain the latest edition. Purchasers of AMPP technical reports may receive current information on all AMPP publications by contacting AMPP Customer Support, 15835 Park Ten Place, Houston, TX 77084-5145 (Tel: +1 281-228-6700, email: customersupport@ampp.org).

Document History:

2023-01-23: Revised by AMPP Standards Committee (SC) 05, Surface Preparation

1996-2001: Developed by SSPC Surface Preparation Group Committee
and NACE Unit Committee T6G on Surface Preparation

AMPP values your input. To provide feedback on this standard, please contact: standards@ampp.org

SSPC-TR 2/NACE TR6G198-2023

©2023 Association for Materials Protection and Performance (AMPP). All rights reserved.

Wet Abrasive Blast Cleaning

Foreword, Scope, Rationale	4
Referenced Standards and Other Consensus Documents	4
Section 1 General	5
Section 2 Classifications of WAB Cleaning Systems	5
Section 3 Descriptions of WAB Nozzles	10
3.1 Conventional Abrasive Blast Nozzle	10
3.2 Pressurized Air Abrasive Blast Cleaning with Water Induction or Injection near the Nozzle.....	10
3.3 Water Blast Cleaning with Air/Abrasive Induction or Injection.....	11
Section 4 Wet Abrasive Cleaning Delivery Systems Comparison.....	12
Section 5 Painting Applications: Procedures and Parameters Bibliography	13
Section 6 Additional Considerations	14
Section 7 Guidance for Surface Cleanliness Using Wet Methods	15
Section 8 Flash Rust.....	16
Section 9 Corrosion Inhibitors/Surfactants/Rinse Aids.....	16
Other Referenced Documents.....	17
Bibliography	17
Figures	
Figure 1 Dry Abrasive System with Water Added at Metering Valve (Type 1 System), Using a Conventional Air Blast Nozzle (Nozzle A).....	5
Figure 2 Dry Abrasive System with Water Added at Exit of the Nozzle (Type 2 System)	7
Figure 3 Water Blast Cleaning with Abrasive Addition (Type 3 System) Using Nozzles D or E.....	8
Figure 4 Hydraulic Systems with Water and Abrasive Mixed in the Vessel, Pressurized by Water (Accelerated by Air) (Type 4 System), Using Nozzle A.....	9
Figure 5 Pneumatic Systems with Water and Abrasive Mixed in the Vessel, Pressurized by Air (Type 5 System) Using Nozzle A.....	9
Figure 6 Conventional Abrasive Blast Nozzle (Nozzle A).....	10
Figure 7 Radial Water Induction (Nozzle B)	10
Figure 8 LP Water/Abrasive Mixed in the Blast Hose (Nozzle C).....	10
Figure 9 LP/ULP Water with Air/Abrasive Induction Nozzle Assembly Fixed Slot (Nozzle D)	11
Figure 10 HP/ULP Water with Air/Abrasive Induction Nozzle Assembly Rotating Internal Nozzle (Nozzle E)	11
Tables	
Table 1 Energy Source and Operating Pressures of Wet Abrasive Blasting Systems.....	12

Foreword

Wet abrasive blast (WAB) cleaning is performed using a mixture of water, air, and abrasives. The water wets the abrasive and helps to substantially reduce dispersion of fine particulates (dust) resulting from the breakup of abrasive media, surface corrosion products, and existing coatings. WAB cleaning is an alternative to dry abrasive blast or waterjet⁽¹⁾ cleaning.

Other generic or manufacturer-specific terms used to describe specific WAB cleaning systems are: fluidized abrasive blast cleaning, water shroud, wet-head blasting, water-enclosed abrasive blasting, wet blasting, low volume water abrasive blasting, slurry blasting, abrasive waterjetting (AWJ), or abrasive injected waterjetting/blasting (AIWJ).

Scope

This technical report discusses equipment, procedures, materials, and the resulting substrate conditions involved in a variety of WAB cleaning methods currently available for commercial use. It also discusses the effect that the water present with these wet cleaning methods has on achieving the defined degree of cleaning of steel surfaces in accordance with the wet abrasive blast cleaning standards found in the list of Referenced Standards and Other Consensus Documents. It is intended for use primarily by specifiers, owners, painting contractors, inspectors, and others involved in surface preparation of industrial structures.

Rationale

This report was originally issued in 1998 and has been revised to include additional configurations of equipment setup as well as current (2022) developments in the design of wet abrasive blast cleaning systems and nozzles. This TR provides a foundation to assist users to determine the quantity and quality of water, abrasive, and air.

AMPP technical reports are intended to convey technical information or state-of-the-art knowledge regarding corrosion. In many cases, they discuss specific applications of corrosion mitigation technology, whether considered successful or not. Statements used to convey this information are factual and are provided to the reader as input and guidance for consideration when applying this technology in the future. However, these statements are not intended to be recommendations for general application of this technology and must not be construed as such.

Referenced Standards and Other Consensus Documents

The latest edition, revision, or amendment of the referenced documents in effect shall govern unless otherwise dated.

AMPP/NACE/SSPC, www.ampp.com

SSPC-AB 1	Mineral and Slag Abrasives
SSPC-AB 3	Ferrous Metallic Abrasive
SSPC-Guide 15	Field Methods for Extraction and Analysis of Soluble Salts on Steel and Other Nonporous Substrates
SSPC-SP 5 (WAB)/NACE WAB-1	White Metal Wet Abrasive Blast Cleaning
SSPC-SP 6 (WAB)/NACE WAB-3	Commercial Wet Abrasive Blast Cleaning
SSPC-SF 7 (WAB)/NACE WAB-4	Brush-Off Wet Abrasive Blast Cleaning
SSPC-SP 8 (WAB)/NACE WAB-8	Industrial Wet Abrasive Blast Cleaning
SSPC-SP 10 (WAB)/NACE WAB-2	Near-White Metal Wet Abrasive Blast Cleaning
SSPC-VIS 1	Guide and Color Reference Photographs for Steel Surfaces Prepared by Dry Abrasive Blast Cleaning

⁽¹⁾ Waterjetting is defined as "use of standard jetting water discharged from a nozzle at pressures of 70 MPa (10,000 psig) or greater to prepare a surface for coating or inspection."² Standard jetting water does not contain sediments or abrasive media.